



Technical Data Sheet

Eastman™ Turbo Oil 2197

Application/Uses

- Aviation
- Engine Accessories
- Engines

Key Attributes

- 5 cSt High Thermal Stability synthetic lubricant
- High temperature cleanliness
- Outstanding Oxidative, Thermal and Hydrolytic stability

Product Description

Eastman™ Turbo Oil 2197 is designed to exceed the demands of current and future jet engines. With over 300 million hours of in-flight experience, it is by far the most widely used HTS fleet oil in the world. Eastman™ Turbo Oil 2197 is manufactured in our own facility so you can rely on consistently high quality wherever you are in the world.

Eastman™ Turbo Oil 2197 is AS5780 HPC / MIL-PRF-23699 HTS class, 5 cSt turbine oil for the most thermally demanding engine and accessory applications.

Typical Properties

Property	Test Method	Typical Value, Units
Density @ 15°C	ASTM D 1298	0.9968 kg/L
Viscosity, Kinematic		
@ 100°C	ASTM D 445	5.28 mm ² /s
@ 40°C	ASTM D 445	26.98 mm ² /s
@ -40°C after 35 minutes	ASTM D 2532	12,539 mm ² /s
Pour Point	ASTM D 97	-57°C
Flash Point	ASTM D 92	262°C
Total Acid Number	SAE ARP5088	0.36 mg KOH/g
Evaporation Loss 6.5 hrs @ 204°C	ASTM D 972	2.30%
Foaming Volume ^a		
Sequence 1 @ 24°C	ASTM D 892	10/0 ml/vol
Sequence 2 @ 93 °C	ASTM D 892	10/0 ml/vol
Sequence 3 @ 24°C	ASTM D 892	10/0 ml/vol
Thermal Stability & Corrosivity ^b		
Viscosity	FED-STD-791, 0.37 3411	
Total Acid Number	FED-STD-791, 1.08 mg KOH/g 3411	
Metal Weight	FED-STD-791, -0.154 mg/cm ² 3411	

Corrosion & Oxidative Stability ^c

Viscosity @ 40°C	FED-STD-791, 14.75% 5308
Total Acid Number	FED-STD-791, 0.96 mg KOH/g 5308
Steel Weight Change	FED-STD-791, 0.011 mg/cm ² 5308
Silver Weight Change	FED-STD-791, -0.017 mg/cm ² 5308
Aluminium Weight Change	FED-STD-791, 0.009 mg/cm ² 5308
Magnesium Weight Change	FED-STD-791, -0.012 mg/cm ² 5308
Copper Weight Change	FED-STD-791, -0.076 mg/cm ² 5308
Sludge	FED-STD-791, 0.37 mg/100ml 5308

Sediment

Visual Undissolved Water	FED-STD-791, None 3010
Sediment, 1.2 µm filter	FED-STD-791, 0.85 mg/L 3010
Metal Weight	FED-STD-791, 0.12 mg/cm ² 3010

a @ 1 minute setting

b @ 274°C

c 72 hrs @ 204°C

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

06-Oct-2014 9:38:05 AM